
	ARIA 55 LOOSELAY		
DESCRIPTION			
Total Thickness	EN ISO 24346	mm	5,00
Thickness of the wearlayer	EN ISO 24340	mm	0,55
Weight	EN ISO 23997	g/m ²	8900
Size	EN ISO 24342	mm	177,8x1219,2 600x600
Number of planks/tiles and sqm per box	-	-	10 / 2,17 m ² 7 / 2,52 m ²
CLASSIFICATION			
Norm/Product Specification	-	-	EN ISO 10582
European Classification	EN ISO 10874	class	33 - 42
Fire Rating	EN 13 501-1	class	Bfl-s1
Static Electrical Propensity	EN 1815	kV	< 2
Electrical Behavior	EN 1081		pass
Slip Resistance Wet	DIN 51 130	class	R10
PERFORMANCES			
Wear Resistance	EN 660.2	mm ³	< 2,0
Wear Group	NF 189	group	T
Dimensional stability	EN ISO 23999	%	≤ 0,25
Residual Indentation	EN ISO 24343-1	mm	≤ 0,10
Castor chair test	ISO 4918	-	OK
Thermal Conductivity	EN ISO 10456	W/(m.K)	0,25
Colour Fastness	EN 20 105 - B02	degree	≥ 6
Surface Treatment	-	-	PUR
Chemical Products Resistance	EN ISO 26987		OK
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 10
CE MARKING			
	EN 14041	